

25/400 Ytterbium-Doped LMA Double Clad Fibers



Coherent's 25/400 Ytterbium-doped double clad fiber is ideally suited for high average power pulsed and narrow linewidth CW fiber amplifier applications. Based on a "few-moded" waveguide structure, this fiber is incorporated into components and monolithic designs where maintaining beam quality can be more difficult. In addition to the standard active fiber, Coherent can supply a matching passive support fiber for component and pigtail development efforts. As with all Coherent standard Large Mode Area (LMA) fibers, these fibers are proof-tested to 100 kpsi, an industry requirement for long term reliability when coiling for mode filtering.

Typical Applications

- High peak power amplifiers
- LIDAR
- Material processing
- Non-linear optics/frequency doubling

Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- LMA core design and short amplifier length — Useful for generating high peak powers
- "Few" moded core design — Easy to maintain single mode LP01 beam through fiber & components
- PANDA-style stress structure for increased birefringence — Superior optical performance and uniformity
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

Optical Specifications

	PLMA-YDF-25/400-VIII	LMA-YDF-25/400-VIII
Operating Wavelength	1060 – 1115 nm	1060 – 1115 nm
Core NA	0.060 ± 0.010	0.060 ± 0.010
First Cladding NA (5%)	≥ 0.46	≥ 0.46
Cladding Attenuation	N/A	≤ 15.0 dB/km @ 1095 nm
Cladding Absorption	0.80 ± 0.10 dB/m at 915 nm 2.40 dB/m near 975 nm	0.60 ± 0.10 dB/m at 915 nm 1.80 dB/m near 975 nm
Birefringence	nominal 3.5×10^{-4}	N/A

Geometrical & Mechanical Specifications

	PLMA-YDF-25/400-VIII	LMA-YDF-25/400-VIII
Cladding Diameter	400.0 ± 15.0 μm	N/A
Cladding Diameter (flat-to-flat)	N/A	400.0 ± 15.0 μm
Core Diameter	25.0 ± 2.5 μm	25.0 ± 1.5 μm
Coating Diameter	550.0 ± 20.0 μm	500.0 ± 20.0 μm
Core Non-Circularity	N/A	≤ 15 %
Coating Material	Low Index Acrylate	Low Index Acrylate
Proof-test Level	≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)

The passive version of each fiber is also available - see PLMA-GDF-25/400 and LMA-GDF-25/400



Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.

25/400 Precision Matched Passive LMA Double Clad Fibers



Coherent's Large Mode Area (LMA) and Polarization Maintaining LMA (PLMA) passive double clad fiber are ideal for high power fiber lasers and amplifiers used in military, industrial, and medical applications. These fibers feature a 25 micron diameter core and 400 micron diameter clad size with a low NA (0.065) core. They are precision matched to their active Yb-doped 25/400 LMA and PLMA matched counterparts to ensure excellent splice compatability and low loss. As with all Coherent standard Large Mode Area (LMA) fibers, these fibers are proof-tested to 100 kpsi, an industry requirement for long term reliability. They utilize the latest fiber design and NuCOAT™ coating technology to ensure excellent preservation of beam quality and extended operating life at the high power levels demanded by today's industrial fiber laser applications. These precision matched fibers are available in both non-PM and PANDA-style PM fibers.

Typical Applications

- High peak power amplifiers
- LIDAR
- Material processing
- Non-linear optics/frequency doubling

Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- LMA core design — Useful for transmitting high CW powers
- “Few” moded core design — Easy to maintain single mode LP01 beam through fiber & components
- PANDA-style stress structure for increased birefringence — Superior optical performance and uniformity
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

Optical Specifications

	PLMA-GDF-25/400-M	LMA-GDF-25/400-M
Operating Wavelength	1060 – 1600 nm	1060 – 1600 nm
Core NA	0.065 ± 0.005	0.065 ± 0.005
First Cladding NA (5%)	≥ 0.46	≥ 0.46
Core Attenuation	≤ 40.0 dB/km @ 1300 nm ≤ 20.0 dB/km @ 1200 nm	≤ 30.0 dB/km @ 1300 nm ≤ 15.0 dB/km @ 1200 nm
Cladding Attenuation	≤ 15.0 dB/km @ 1095 nm	≤ 15.0 dB/km @ 1095 nm
Birefringence	nominal 3.5×10^{-4}	N/A

Geometrical & Mechanical Specifications

	PLMA-GDF-25/400-M	LMA-GDF-25/400-M
Cladding Diameter	395.0 ± 10.0 μm	395.0 ± 5.0 μm
Core Diameter	25.0 ± 1.5 μm	25.0 ± 1.5 μm
Coating Diameter	550.0 ± 15.0 μm	550.0 ± 15.0 μm
Core/Clad Offset	≤ 2.00 μm	≤ 2.00 μm
Clad Non-Circularity	N/A	≤ 0.5 %
Proof-test Level	≥ 100 kpsi (0.7 GN/m ²)	≥ 100 kpsi (0.7 GN/m ²)



These precision matched fibers are included in our precision matched sets - see PLMA-YDF-25/400-M and LMA-YDF-25/400-M

Nufern • 7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • Email: tech.sales@coherent.com
www.coherent.com ; www.shop.coherent.com • Coherent products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Coherent can assist with your requirements.